

No Post Cure
Silicone elastomer

SH2540U



FEATURES

No post cure

BENEFITS

- Excellent heat resistance
- Excellent low compression set
- Excellent mechanical properties

COMPOSITION

- Silicone polymer
- Silica

1. Product Description

SH2540U is one of the series of no post cure general purpose and high modulus silicone rubber bases

2. Applications

Extrusion, tubing and profiles
Molding, Calendering and Sheeting

3. Key Performance Properties

Heat and reversion stabilized
40 durometer grade available
Good resistance to fluids.
High elasticity and very low compression set.

4. Typical Property Data

		SH2540U
Uncured compound		
Appearance		Beige
Williams Plasticity		150
Cured compound (1st cure 10min at 170 °C)		
Curing agent		2,5-dimethyl-2,5-t-butylhexane peroxide
Content of Curing agent phr		1.0
Mechanical properties (JIS K6249)		
Specific gravity(25 °C)		1.10
Hardness (Type A)		42
Tensile strength	Mpa	8.3
Elongation	%	600
Tear strength	N/mm	29
Compression set	%	14
Linear shrinkage	%	3.7
Heat aged compound (250°C 72hr)		
Hardness (Type A)		36
Tensile strength	Mpa	6.2
Elongation	%	550

Caution) Typical property data values should not be used as specifications

No Post Cure
Silicone elastomer

SH2540U



5. How to use

For blending or pigmenting, milling with two-roll mill is the most suitable Process. Milling time should be carefully decided to secure uniformity of Materials.

6. Handling Precautions

Wear eye protection and protective glove when handling this product

7. Safety and Storage

Use it within 12 months from the date of manufacture

Store in a cool dry place out of direct sunlight

Keep out of the reach of the children

8. Packaging

20 kg box

9. Warranty Information – *Please read carefully*

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KCC's products are safe, effective, and fully satisfactory for the intended end use.

KCC's sole warranty is that the product will meet the KCC sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to replacement of any product shown to be other than as warranted.

KCC specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KCC provides you with a specific, duly signed endorsement of fitness for use, KCC disclaims liability for any incidental or consequential damages.

Suggestions of use shall not be taken as inducements to infringe any patent.

10. The date of issue

The first of issue : 2009.03.01

The revised of issue : 2009.04.01 (1st)

※ Please refer to MSDS if you want to know more specific usage or caution.
for further information, please see our website, www.kccworld.co.kr