

|           |                       |         |
|-----------|-----------------------|---------|
| Ethylene  | <b>KP KEP Series</b>  | Product |
| Propylene | ISO 9001<br>ISO 14001 | Data    |
| Rubber    | Certified by DNV      | Sheet   |

## KEP-110

### Features :

- Low Mooney Viscosity EPM Grade
- Amorphous
- Good processing & easy mill handling
- Excellent heat resistance

### Characteristics :

- Ethylene Content : Low
- Molecular Weight Distribution : Broad
- Specific Gravity : 0.86

### Applications :

Heat resistant belt, electricals, brake parts  
TPO, adhesives, binder, oil additives, gasket

| Test Items                           | Sales Specifications | Test Methods                             |
|--------------------------------------|----------------------|--|
| Volatile Content (wt.%)              | 1.00max              | ASTM D5668                               |
| Ethylene Content (wt.%)              | 51.5±3.0             | ASTM D3900                               |
| Raw Mooney Viscosity<br>(ML1+4,100 ) | 40.0±5.0             | ASTM D1646<br>(Polymer remassed at 140 ) |

Last updated September 7. 2007

|             |   |
|-------------|---|
| Revision No | 2 |
|-------------|---|

H.R. Koo / Manager,  
R&D Center

